

AMENDED CLAIM SET:

E | 1. (currently amended) A method for producing a molded article of a modified polytetrafluoroethylene by joining, comprising the steps of:

providing at least two premolded parts of modified polytetrafluoroethylene having different coefficients of thermal shrinkage wherein each of said at least two premolded parts has a coefficient of thermal shrinkage in the range between 0.2 and 10 %, and allowing


arranging their joining faces to be in contact with each other or to be closely placed, and

sintering the parts to join them at the joining faces.

2. (currently amended) The method of A method according to claim 1, wherein the joining of said at least two premolded parts at the joining faces is carried out without the application of an external pressure.

3. (currently amended) The method of A method according to claim 1, wherein each of said at least two premolded parts has a coefficient of thermal shrinkage in the range between 0.2 and 10, and the difference in the coefficient of thermal shrinkage between two premolded parts which are adjacently placed ranges from 0.2 to 9.8.

4. (currently amended) The method of A method according to claim 1, wherein at least one premolded part is surrounded by another premolded part having a larger coefficient of thermal shrinkage than that of the premolded part which it surrounds.

 5. (new) The method of claim 1, wherein said at least two premolded parts of modified polytetrafluoroethylene having different coefficients of thermal shrinkage are prepared by (A) separately molding two or more modified PTFE powders having the same molecular weight but different particle sizes or by (B) molding portions of the same modified PTFE powder under different pressures or by (C) molding an as-polymerized modified PTFE and by molding a granulated product of the same modified PTFE powder.
